



REQUIREMENT	TYPICAL VALUES		
	Imperial	Metric	
Rockwell Hardness	80 - 90 Rockwell M.	80 - 90 Rockwell M.	
Density	0.045 – 0.49 lbs/in ³	1.25 – 1.40 (Gms/cc)	
Tensile Strength			
Lengthwise	9427 PSI	65 N/mm ²	
Crosswise	8700 PSI	60 N/mm ²	
Flexural Strength			
Lengthwise	20.000 PSI	138 N/mm ²	
Crosswise	15.500 PSI	107 N/mm ²	
Shear Strength			
	19.500 PSI	134 N/mm ²	
Compressive Strength			
Flatwise	50.000 PSI	345 N/mm ²	
Edgewise	19600 PSI	135 N/mm ²	
Water Absorption, Volumetric			
	Less than 0.1%	Less than 0.1%	
Coefficient of Thermal Expansion 20 - 100°C (Per °C x 10 ⁻⁵)			
	Parallel to Laminations	6 - 7	
	Right Angle to Laminations	12 - 13	
Max Constant Operating Temp			
	212°F	100°C	
Min Constant Operating Temp			
	-94 °F	-70°C	
Tensile Modulus			
	0.47 (lbs/in ² x 10 ⁶)	0.32 (N/mm ² x 10 ⁴)	
Lubricants			
	Moly + PTFE	Moly + PTFE	
Colour			
	Light Grey	Light Grey	
Coefficient of Friction, Tufcot against Stainless Steel			
Bearing Pressure 15.5 N/mm ²	Dry	0.10 – 0.12	0.10 – 0.12
Surface Speed 2.20 M/Sec	Water	0.01	0.01
	Oil	0.02	0.02

The information contained on this document is considered proprietary to our company in that these items, compounds and processes were developed at private expense. This information shall not be released, disclosed or duplicated for procurement or manufacturing, reproduction hereof, in whole or in part, shall be marked with this legend.

The information in this data sheet is based on many decades of experience in the manufacturing and application of our products. However, unknown parameters and conditions may restrict general statements during usage. It is vital that customers satisfy themselves as to the suitability of individual products through adequate testing. For these reasons and due to the wide range of applications of our products, Tufcot can accept no liability as to the suitability or correctness of our recommendations in individual cases. For specific operating conditions please discuss your requirements with Tufcot at the quotation stage.