



REQUIREMENT	TYPICAL VALUES		
	Imperial	Metric	
<b>Rockwell Hardness</b>	95 - 100 Rockwell M.	95 - 100 Rockwell M.	
<b>Density</b>	0.054/ 0.055 lbs/in <sup>3</sup>	1.5 – 1.52 (Gms/cc)	
<b>Tensile Strength</b>			
Lengthwise	9427 PSI	65 N/mm <sup>2</sup>	
Crosswise	8700 PSI	60 N/mm <sup>2</sup>	
<b>Flexural Strength</b>			
Lengthwise	20.000 PSI	138 N/mm <sup>2</sup>	
Crosswise	15.500 PSI	107 N/mm <sup>2</sup>	
<b>Shear Strength</b>	19.500 PSI	134 N/mm <sup>2</sup>	
<b>Compressive Strength</b>			
Flatwise	50.000 PSI	345 N/mm <sup>2</sup>	
Edgewise	20.000 PSI	138 N/mm <sup>2</sup>	
<b>Water Absorption, Volumetric</b>	Less than 0.1%	Less than 0.1%	
<b>Coefficient of Thermal Expansion</b> 20 - 100°C (Per °C x 10 <sup>-5</sup> )	Parallel to Laminations	6 - 7	
	Right Angle to Laminations	12 - 13	
<b>Max Constant Operating Temp</b>	212°F	100°C	
<b>Min Constant Operating Temp</b>	-94 °F	-70°C	
<b>Flexural Modulus</b>	0.47 (lbs/in <sup>2</sup> x 10 <sup>6</sup> )	0.32 (N/mm <sup>2</sup> x 10 <sup>4</sup> )	
<b>Resin System</b>	Self-Extinguishing Fire Retardant Grade		
<b>Lubricants</b>	Graphite	Graphite	
<b>Colour</b>	Light Grey	Light Grey	
<b>Coefficient of Friction, Tufcot against Stainless Steel</b> Bearing Pressure 15.5 N/mm <sup>2</sup> Surface Speed 2.20 M/Sec	Dry	0.15 – 0.14	0.15 – 0.14
	Water	0.01	0.01
	Oil	0.02	0.02

**The above values are typical**

The information contained on this document is considered proprietary to our company in that these items, compounds and processes were developed at private expense. This information shall not be released, disclosed or duplicated for procurement or manufacturing, reproduction hereof, in whole or in part, shall be marked with this legend.

The information in this data sheet is based on many decades of experience in the manufacturing and application of our products. However, unknown parameters and conditions may restrict general statements during usage. It is vital that customers satisfy themselves as to the suitability of individual products through adequate testing. For these reasons and due to the wide range of applications of our products, Tufcot can accept no liability as to the suitability or correctness of our recommendations in individual cases. For specific operating conditions please discuss your requirements with Tufcot at the quotation stage.